

We are binding

# Mowital<sup>®</sup> – PVB for every challenge

***kuraray***

**Mowital<sup>®</sup>**

# The material for thousand applications

**Mowital®**  
for 3D  
printing

**Mowital®**  
for  
ceramics

**Mowital®**  
for printing  
inks

**Mowital®**  
for  
coatings


## FROM PAINTS AND PRINTING INKS, TO ADHESIVES, CERAMICS, FILMS AND 3D PRINTING:

Polyvinyl butyral resins (PVB) are extremely important in many areas today. With **Mowital®**, Kuraray offers an unique portfolio of PVB materials.

Thanks to their specific acetal, hydroxyl and acetate groups, they feature technical and chemical properties that are ideally tailored to a wide range of applications.

Benefit from the versatility and quality of European market leader for technical PVB applications Kuraray that set standards across the globe.

learn more:



# Mowital® – the PVB for every challenge



**WITH ITS NUMEROUS PRODUCT VARIANTS, MOWITAL® IS THE FIRST CHOICE FOR A WIDE RANGE OF APPLICATIONS:**

- Compatible with many **polymers**, **Mowital®** enables ideal crosslinking of various functional groups of organic substances.
- The PVB is ideal for use with a **wide range of solvents** – from non-polar solvents like hydrocarbons to highly polar solvents like methanol.
- **Mowital®** is available in variants with **different viscosities**, from low to high viscous grades.

#### **FOOD CONTACT STATUS**

The use of **Mowital®** B types is sanctioned by: The (EG) regulation 1935/2004 and No. 10/2011 – all monomers and starting substances authorised by listing in Annex I. Council of Europe, Resolution AP 96(5) on surface coatings intended to come into contact with foodstuffs – all monomers and starting substances authorised by listing in appendix 2, list 1. US Food and Drug Administration 21 CFR § 175.105 adhesives, 21 CFR § 175.300 resinous and polymeric coatings, 21 CFR § 176.170 components of paper and paperboard in contact with aqueous and fatty foods.

# Properties for the highest of requirements

water sensitivity

high binding power

excellent adhesion

elasticity

colourless



**Mowital®** features outstanding optical properties. It is **colourless**, perfect for coatings and lending paints and printing inks a brilliant gloss. As a film it is crystal clear, similar to glass.



Thanks to its **high binding power** and rheological properties, **Mowital®** acts as an excellent binder for printing inks, paints and coatings as well as in the production of ceramic products.



For optimised **water sensitivity** the special polymer is optionally available with a higher number of butyral groups.



With excellent **adhesion and film formation properties**, **Mowital®** is ideal for use in adhesives. It forms an ideal bond to a diversified spectrum of surfaces, both organic and inorganic substrates.



**Mowital®** is a rheological modifier. With its **outstanding elasticity**, it gives plastics and adhesive systems excellent softness and flexibility.



**Mowital®** is particularly suited for **thermoplastic applications**.

## Applications of Mowital®

● Main application Area ○ Possible application Area	Mowital® B 14 S	Mowital® B 16 H	Mowital® B 20 H	Mowital® B 30 T	Mowital® B 30 H	Mowital® B 30 HH	Mowital® B 45 H	Mowital® B 60 T	Mowital® B 60 H	Mowital® B 60 HH	Mowital® B 75 H	Mowital® BA 20 S	Mowital® BA 55 HH	Mowital® SB 70 HH
Strippable packaging coatings	●	●	●		●	●						●		
Automotive refinishing coatings	○	○	○		●	●	○		○	○		○	○	
Can coating/Stoving enamels/Film lacquers	○	○	○	●	●	●	○	●	○	○	○	●	○	
Electrostatic spray primers						●				●		○	●	
Corrosion protection/shop primers/wash primers	●	●	●		●	●	●		●	●		●	●	
Heat-sealable lacquers	●	●	●	●	●	●	●	●	●	●	●	●	●	
Radiator primers/topcoats	●	●	●		●	●	●		●	●		●	●	
Wood sealing varnishes	●	●	●		●	●	●		●	●		○	●	
Plastic surface finishes/nitrocellulose lacquers	●	●	●		●	●	●	●	○	○		●	●	
Gear paints/paper varnishes	●	●	●		●	●	●	●	●	●		○	●	
Adhesives/oil-resistant lacquers	●	●	●		●	●	●	●	●	●		○	●	
Road marking paints	●	●	●		●	●	○	○	○	○		○		
Additive for powder coatings	●	●	●	○	●	○		○				●		
Coil coatings	●	●	●	●	●	○	●	●	●	○		●	○	
Zinc-rich primers	○	○	○		●	●						●		
Inkjet printing inks	●	●	●									●		
Flexographic/special gravure inks	●	●	●		●							●		
Pigment preparations	●	●	●	○	●	○	○					●		
Thermo-transfer inks	○	○	○		●	○	●		●	○		●	●	
Temporary binder for ceramics					○	○	●		●	●	●		●	●
Foundry aids					●	○	●					○		
Adhesive additives/rheology modifiers	○	○	○	○	○	○	●	●	●	●	○	●	●	
Hotmelts	●	●	●		●	●	●		●	●	○	●	●	
Binder for abrasive papers					○	○	○		●	●	○		●	
Light bulb cement	○	○	○		●	○	●		○	○			○	
Structural adhesives	○	○	○		○	●	○		●	●	●	○	●	
Cardboard packaging impregnations	●	●	●		●	●	●		○	○		●		
Candle coatings	○	○	○		○	○	●		●	●		○	●	
Prepregs/Composites							●	●	●	●	●		●	
Thermoplastic processing	●	●	●	●	●	●	●	●	●	●	●	●	●	●
3D Printing					●	○	●		●	○				

Mowital® B = Homo acetal → acetalisation of butyraldehyde

Mowital® BA = Mixed acetal → co-acetalisation of butyraldehyde and acetaldehyde

Mowital® SB = Homo acetal → acetalisation of butyraldehyd and extra specification

## Analytical Data of PVB

Grade	Dynamic viscosity (10 % ethanol) Hoeppler method (20 °C) [mPa · s]	Corresponding viscosity range <sup>2</sup> (10 % ethanol/ toluene 1:1) Brookfield method (20 °C / 30 rpm) [mPa · s]	PVOH content (Hydroxyl)		PVOAc content (Acetate)		Glass transition temperature = Tg °C	Non- volatile content [wt-%]
			[wt-%]	[mol-%]	[wt-%]	[mol-%]		
			Mowital® B 14 S	9,0–13,0	6,5–8,5	14,0–18,0		
Mowital® B 16 H	14,0–20,0	9,0–14,0	18,0–21,0	26,2–30,2	1,0–4,0	0,7–2,9	63	≥ 97,5
Mowital® B 20 H	20,0–30,0	14,0–23,0	18,0–21,0	26,2–30,2	1,0–4,0	0,7–2,9	64	≥ 97,5
Mowital® B 30 H	35,0–60,0	24,0–42,0	18,0–21,0	26,2–30,2	1,0–4,0	0,7–2,9	68	≥ 97,5
Mowital® B 30 HH	35,0–60,0	23,0–41,0	11,0–14,0	16,7–20,9	1,0–4,0	0,8–3,1	63	≥ 97,5
Mowital® B 30 T	30,0–55,0	26,0–50,0	24,0–27,0	33,8–37,6	1,0–4,0	0,7–2,9	70	≥ 97,5
Mowital® B 45 H	60,0–90,0	36,0–54,0	18,0–21,0	26,2–30,2	1,0–4,0	0,7–2,9	69	≥ 97,5
Mowital® B 60 H	160,0–260,0	120,0–200,0	18,0–21,0	26,2–30,2	1,0–4,0	0,7–2,9	70	≥ 97,5
Mowital® B 60 HH	120,0–280,0	80,0–190,0	12,0–16,0	18,1–23,7	1,0–4,0	0,8–3,0	65	≥ 97,5
Mowital® B 60 T	180,0–280,0	160,0–260,0	24,0–27,0	33,8–37,6	1,0–4,0	0,7–2,9	72	≥ 97,5
Mowital® B 75 H <sup>1</sup>	60,0–100,0	44,0–75,0	18,0–21,0	26,2–30,2	0,0–4,0	0,0–2,9	73	≥ 97,5
Mowital® BA 20 S	24,0–30,0	15,0–20,0	14,0–18,0	20,8–26,3	1,0–4,0	0,8–3,0	84	≥ 97,5
Mowital® BA 55 HH	160,0–220,0	95,0–135,0	11,0–14,0	16,7–20,9	1,0–4,0	0,8–3,1	92	≥ 97,5
Mowital® SB 70 HH	280,0–330,0	155,0–185,0	12,0–14,0	18,1–20,9	1,0–4,0	0,8–3,1	68	≥ 97,5

<sup>1</sup> 5 % Viscosity<sup>2</sup> CalculatedDegree of  
acetalisation

high

medium


low

Residual PVA  
content

low

medium

high



## Solubility of Mowital®

● Unlimited Solubility ○ Limited Solubility — Insoluble	Mowital® T-grades OH Content: 24–27 %	Mowital® H-grades OH Content: 18–21 %	Mowital® S-grades OH Content: 14–18 %	Mowital® HH-grades OH Content: 11–14 %
<b>ALCOHOLS</b>				
Methanol	●	●	○	○
Ethanol	●	●	●	●
Propanol	●	●	●	●
i-Propanol	●	●	●	●
Butanol	●	●	●	●
i-Butanol	●	●	●	●
Diacetone alcohol	●	●	●	●
Benzyl alcohol	●	●	●	●
<b>GLYCOL ETHERS</b>				
1-Methoxy propanol-2	●	●	●	●
Butyl glycol	●	●	●	●
3-Methoxy-butanol-1 (methoxy butanol)	●	●	●	●
Dowanol (DPnB)	○	●	●	●
<b>ETHERS</b>				
Dioxane	●	●	●	●
Tetrahydrofuran (THF)	●	●	●	●
<b>CELLUSOLVE™</b>				
Methyl Cellusolve	●	●	●	●
Ethyl Cellusolve	●	●	●	●
Butyl Cellusolve	●	●	●	●
<b>ESTERS</b>				
Methoxy propyl acetate	—	●	●	●
Methyl acetate	—	○	●	●
Butyl acetate	—	●	●	●
Acetic acid-methoxy-n-butylester (Butoxyl)	—	○	●	●
Glycolic acid-n-butylester (Polysolvan 0)	●	●	●	●
Dibasic esters (DBE)	—	●	●	●
Ethyl lactate	●	●	●	●
<b>KETONES</b>				
Acetone	—	●	●	●
Methylethylketone	○	●	●	●
Methylisobutylketone	—	●	●	●
Cyclohexanone	●	●	●	●
<b>HYDROCARBONS</b>				
Aliphatic	○ <sup>1)</sup>	○ <sup>1)</sup>	○ <sup>1)</sup>	○ <sup>1)</sup>
Toluene	—	○ <sup>1)</sup>	○ <sup>1)</sup>	○ <sup>1)</sup>
Xylene	—	○ <sup>1)</sup>	○ <sup>1)</sup>	○ <sup>1)</sup>
<b>OTHERS</b>				
Terpineol	●	●	●	●
Butyl carbitol	●	●	●	●
Acetic Acid	●	●	●	●
Dimethyl sulfoxide (DMSO)	●	●	●	●

<sup>1)</sup> Completely soluble if solvent contains 10 % alcohol.

The solubilities stated here refer to the pure solvents (determined in 10 % solution – for B 75 H in 5 % solution). In many cases solvent blends have superior dissolving capacity.

**Kuraray Europe GmbH**  
Philipp-Reis-Str. 4  
65795 Hattersheim am Main  
Germany

marketing-pvb@kuraray.com  
[www.mowital.com](https://www.mowital.com)

Copyright ©2021 Kuraray. All rights reserved.

Mowital is a registered trademark of Kuraray Europe GmbH. The information, recommendations and details given in this document have been compiled with care and to our best knowledge and belief. They do not entail an assurance of properties above and beyond the product specification. The user of our products is responsible for ensuring that the product is suitable for the intended use and conforms to all relevant regulations. Kuraray Co., Ltd. and its affiliates do not accept any guarantee or liability for any errors, inaccuracies or omissions in this document. 24.10.2021

**kuraray**